



Composition

Copolymer rubber of chlorinated isobutylene-isoprene with low Mooney viscosity

Basic Properties	Unit	Standard	Test Method
Product Form		Off-white bales	Visual
Volatiles	wt%	%	GB/T 24131.2
MooneyViscosity L1+8,125)	MU	34-42	GB/T1232.1
Total Ash	wt%	%	GB/T 4498.1
Chlorine Content	wt%	1.15-1.35	Q/XH-FX 100
Antioxidant (Non-staining)	wt%	0.02~0.12	YBX-2004
Calcium stearate	wt%	2.0	Q/XH-FX109

Cure Characteristics	Unit	Standard	Test Method
----------------------	------	----------	-------------